

TERMO XT 32

TYPICAL CHARACTERISTICS		
Characteristics	Test Method	TERMO XT 32
ISO Viscosity Grade		32
Density at 15 °C, kg/l	ASTM D - 4052	0.8360
Kinematic Viscosity at 40 °C, cSt	ASTM D - 445	34.20
at 100 °C, cSt	ASTM D - 445	6.42
Viscosity Index	ASTM D - 2270	143
ASTM Colour	ASTM D - 1500	L 0.5
Flash Point (COC), °C	ASTM D - 92	244
Pour Point, °C	ASTM D - 5950	-18
Total Acid Number, mgKOH/g	ASTM D - 664	0.005